



Materials Testing and Research Center

6991 Old 3C Highway
Westerville, OH 43082, USA

Phone: 800-999-5442 x1323
Fax: 614-895-5610

ASTM C-24 Pyrometric Cone Equivalent (PCE)

Material: Mortar
Preparation: Ground to -70 mesh

Customer: Flame Tech
Customer PO: J. Lynch
Date: September 24, 2009

Sample ID	PCE Value	Deformation Temp. (°F)	Comments
Fire Patch	17-18	2754 - 2772	
Sample B	16-17	2716 - 2754	
Sample C	16-17	2716 - 2754	