

ASTM G21-09

Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi

FINAL REPORT: R2017-14-2

AMENDMENT TO R2017-14

Prepared for:
Everkem
5180 Indiana Ave.
Winston Salem, NC 27106

Accredited Testing Provided by:



130 Erick Street
Crystal Lake, IL 60014
815.526.0954
TESTING CERT: #2832.01

Testing Initiated: January 26, 2017
Testing Completed: February 23, 2017
Report Issued: March 1, 2017

Performed By: Marcy Aaron
Title: Staff Technologist

Approved By: Debbie Koester
Title: Quality Manager



Objective:

To evaluate the mold resistance properties of one sample as seen in the ASTM G21 fungal resistance test.

Test Sample Identification:

1. SS90

Test Procedure Summary:

Samples are placed onto the surface of ASTM G21 nutrient salts agar and sprayed with a mixed spore suspension of five fungal strains. The nutrient salts agar provides all of the trace nutritional elements needed by fungi to support growth. However, to achieve a heavy growth, the fungi must use the test material as its primary carbon source. Inoculated samples are incubated and then examined for fungal growth.

Test Variables

	<i>Aspergillus brasiliensis</i> ¹	ATCC 9642
	<i>Penicillium funiculosum</i> ²	ATCC 11797
Test Organisms:	<i>Chaetomium globosum</i>	ATCC 6205
	<i>Trichoderma virens</i> ³	ATCC 9645
	<i>Aureobasidium pullulans</i>	ATCC 15233
Sample Description:	Semi-liquid product prepared for testing by MicroStar*	
Number of Replicates per Sample:	Three	
Positive Growth Control:	Sterile Filter Paper	
Media Used:	Nutrient-Salts Agar prepared according to standard	
Environmental Conditions:	28 - 30°C; ≥85% relative humidity	
Incubation Duration:	28 days	
Deviations from Standard Test Method:	None, testing performed per ASTM G21 without deviation.	

¹ Historically known as *Aspergillus niger*
² Historically known as *Penicillium pinophilum*
³ Historically known as *Gliocladium virens*

*Replicates were prepared by applying the sample to a 2" x 2" polyester panel piece. The sample was spread in an evenly coated layer and allowed to dry for 7 days prior to testing.



Results:

The results for the test pieces can be found in the data table below. The filter paper control pieces had copious fungal growth at Day 14. Temperature and relative humidity were maintained for the duration of the test. These results pertain only to the samples tested.

At week 4, samples rating a “0” or “1” were examined microscopically to confirm the ratings.

The rating scale for this test is as follows:

Rating	Observed Growth
0	No Growth
1	Trace of Growth (less than 10% coverage)
2	Light Growth (10-30% coverage)
3	Medium Growth (30-60% coverage)
4	Heavy Growth (60-100% coverage)

Sample Identification	Rep	Week 1	Week 2	Week 3	Week 4
SS90	1	0	0	0	0
	2	0	0	0	0
	3	0	0	0	0