

November 21, 2017

David Gorrell
Everkem Diversified Products Inc
5180 Indiana Ave
Winston Salem, NC 27106

Subject: Project 18729-010AA - Test Results

Thank you for choosing UL Environment, and its ISO/IEC 17025 accredited testing laboratory, for your analytical needs. Everkem Diversified Products Inc's "SoundSeal 90" was tested by our laboratory for low emitting materials.

Testing was conducted in small environmental chambers following the principles of ASTM D 5116 with the defined product specific test protocols and IAQ emission requirements of the State of California's Indoor Air Quality Program, "Standard Method for the Testing and Evaluation of Volatile Organic Chemical Emissions from Indoor Sources using Environmental Chambers" (aka CA Section 01350).

Calculations were performed using the parameters below to estimate the concentrations of VOCs of concern for use in a classroom environment and in an office environment.

| Ventilation Rate | Room Volume | Product Surface Area |
|---------------------------------|--|----------------------|
| CLASSROOM | | |
| 0.82 air changes per hour (ACH) | 12.2 m x 7.32 m x 2.59 m = 231 m ³ (40 x 24 x 8.5 ft = 8,160 ft ³) | 39 m |
| PRIVATE OFFICE | | |
| 0.68 air changes per hour (ACH) | 3.66 m x 3.05 m x 2.74 m = 30.6 m ³ (12 x 10 x 9 ft = 1,080 ft ³) | 14.6 m |

The product mentioned above as received and tested meets the Section 1350 requirements for use in a classroom and in an office with the above parameters.

If you have any questions or concerns about the test results, please contact your Account Manager at (888) 485-4733.

Sincerely,

Allyson M. McFry

allyon Mcfry

Chemistry Laboratory Director

This report shall not be reproduced, except in full, without permission from UL. Results contained within this report only apply to the actual product tested under the testing conditions documented in this report.

Date Prepared: November 21, 2017
Product #: 18729-010AA
Report #: 18729-01

©2017 UL LLC



INDOOR AIR QUALITY EVALUATION FOLLOWING THE REQUIREMENTS OF CDPH/EHLB/STANDARD METHOD

PREPARED FOR: EVERKEM DIVERSIFIED PRODUCTS INC

MANUFACTURER INFORMATION

| Manufacturer | Everkem Diversified Products Inc |
|------------------------|---|
| Contact Name and Title | David Gorrell, Quality Assurance Director |
| Contact Address | 5180 Indiana Ave Winston Salem, NC 27106 |
| Contact Phone Number | (800) 638-3160 |

PRODUCT INFORMATION

| Product Description | SoundSeal 90 |
|-------------------------|--------------------------------|
| Manufacturer Product ID | Not provided |
| Product Category | Adhesives/Sealants |
| Product Sub-Category | General Construction Adhesives |
| Manufacturing Location | Not provided |
| Date Manufactured | September 14, 2017 |
| Date Collected | October 13, 2017 |
| Date Shipped | October 13, 2017 |
| Date Received | October 16, 2017 |

Released by:

Allyson M. McFry Chemistry Laboratory Director

©2017 UL LLC

EXECUTIVE SUMMARY

PROJECT DESCRIPTION

UL Environment, and its ISO/IEC 17025 accredited testing laboratories, presents the results of its indoor air evaluation of a product identified as "SoundSeal 90" submitted by Everkem Diversified Products Inc. UL Environment conducted this study using a product evaluation test protocol following California's "Standard Method for the Testing and Evaluation of Volatile Organic Chemical Emissions from Indoor Sources using Environmental Chambers" (aka CA Section 01350) (1). Test chamber methodology followed the guidance of ASTM D 5116 (2), volatile organic compound (VOC) analysis followed the methodology in EPA TO-17 (3) and ASTM D 6196 (4), and analysis for low molecular weight aldehydes, including formaldehyde and acetaldehyde, followed the methodology in ASTM D 5197 (5). The definition for total VOCs (TVOC) is from ISO 16000-6 (6). The quantifiable level for all compounds is 2 μg/m³. All identified target list compounds are quantified using authentic standards. Identified substances not on one of the designated toxics list are quantified using either authentic standards or surrogates and are notated appropriately.

The product was monitored for emissions of TVOC, individual VOCs, formaldehyde and other aldehydes over the 96-hour test period. Measurements were made and predicted exposures were calculated according to the CA Section 01350 protocol. As specified in this protocol, the results at 96 hours, after 10 days of conditioning, were compared to ½ (one-half) the current Chronic Reference Exposure Levels (CRELs), as adopted from the California OEHHA list (7). All identified VOCs were also compared to the California-EPA OEHHA Proposition 65 list (8) and the California-EPA Air Resource Board list of Toxic Air Contaminants (TACs) (9).

RESULTS

The calculation parameters and results for the tested product identified as "SoundSeal 90" are shown below:

| Environment | Ventilation Rate (ACH) | Room Volume | Product Usage | Product Surface Area | Product Compliance? |
|-------------|------------------------------|--|------------------|----------------------------|------------------------|
| CLASSROOM | 0.82 | 12.2 m x 7.32 m x 2.59 m = 231 m ³ (40 x 24 x 8.5 ft = 8,160 ft ³) | Sealant | 39 m | Yes |
| OFFICE | 0.68 | 3.66 m x 3.05 m x 2.74 m = 30.6 m ³ (12 x 10 x 9 ft = 1,080 ft ³) | Sealant | 14.6 m | Yes |

©2017 UL LLC

TABLE 1

ENVIRONMENTAL CHAMBER STUDY PARAMETERS PREPARED FOR: EVERKEM DIVERSIFIED PRODUCTS INC

PRODUCT 18729-010AA

Product Description: ADHESIVES/SEALANTS; SoundSeal 90

Date Received at UL Environment: October 16, 2017

Sample Preparation: The product was received by UL Environment as packaged

and shipped by the customer. The package was visually inspected and stored in a controlled environment immediately following sample check-in. Just prior to loading, a $\frac{3}{8}$ " wide bead 11.5" long was applied to a foil-wrapped plate. The sample was immediately placed inside the environmental

chamber, and tested according to the specified protocol.

Conditioning Period: 10/26/2017 - 11/05/2017

Test Period: 11/05/2017 - 11/09/2017

Product Area Exposed: one-sided area = 0.2920 m

Chamber Volume: 0.0867 m³

Product Loading Ratio: 3.37 m/m³

Test Chamber Conditions: Air change rate: $1.00 \pm 0.05 \text{ 1/h}$

Inlet air flow rate: $0.0867 \pm 0.004 \text{ m}^3/\text{h}$

Temperature*: 21.3°C - 22.3°C Relative Humidity: 50% RH ± 5%

^{*}Actual temperature range was outside 23°C ± 1.0°C

Date Prepared: November 21, 2017 Product #: 18729-010AA Report #: 18729-01

©2017 UL LLC

TABLE 2

COMPARISON OF DATA TO CA SECTION 01350 TARGET CRELS AT 96 HOURS FOLLOWING 10 DAYS OF CONDITIONING

PREPARED FOR: EVERKEM DIVERSIFIED PRODUCTS INC PRODUCT 18729-010AA; SOUNDSEAL 90

| Compound Name | CAS Number | ½ CREL (µg/m³) | Chamber Concentration (µg/m³) | Emission Factor ^{††} (µg/m•hr) | Classroom Predicted Concentration (µg/m³)** | Office Predicted Concentration (µg/m³)** | Meets ½ CREL? (Classroom/ Office) |
|---|---------------|----------------------|-------------------------------------|---|--|---|-----------------------------------|
| Acetaldehyde | 75-07-0 | 70 | BQL | BQL | | | Yes |
| Benzene | 71-43-2 | 1.5 | BQL | BQL | | | Yes |
| Carbon disulfide | 75-15-0 | 400 | BQL | BQL | | | Yes |
| Carbon tetrachloride | 56-23-5 | 20 | BQL | BQL | | | Yes |
| Chlorobenzene | 108-90-7 | 500 | BQL | BQL | | | Yes |
| Chloroform | 67-66-3 | 150 | BQL | BQL | | | Yes |
| Dichlorobenzene (1,4-) | 106-46-7 | 400 | BQL | BQL | | | Yes |
| Dichloroethylene (1,1) | 75-35-4 | 35 | BQL | BQL | | | Yes |
| Dimethylformamide (N,N-) | 68-12-2 | 40 | BQL | BQL | | | Yes |
| Dioxane (1,4-) | 123-91-1 | 1,500 | BQL | BQL | | | Yes |
| Epichlorohydrin* | 106-89-8 | 1.5 | BQL | BQL | | | Yes |
| Ethylbenzene | 100-41-4 | 1,000 | BQL | BQL | | | Yes |
| Ethylene glycol | 107-21-1 | 200 | BQL | BQL | | | Yes |
| Ethylene glycol monoethyl ether acetate | 111-15-9 | 150 | BQL | BQL | | | Yes |
| Ethylene glycol monoethyl ether | 110-80-5 | 35 | BQL | BQL | | | Yes |

Date Prepared: November 21, 2017 Product #: 18729-010AA Report #: 18729-01

©2017 UL LLC

| Compound Name | CAS Number | ½ CREL (μg/m³) | Chamber Concentration (µg/m³) | Emission Factor ^{††} (µg/m•hr) | Classroom Predicted Concentration (µg/m³)** | Office Predicted Concentration (µg/m³)** | Meets ½ CREL? (Classroom/ Office) |
|--|---------------|----------------------|-------------------------------------|---|--|---|-----------------------------------|
| Ethylene glycol monomethyl ether acetate | 110-49-6 | 45 | BQL | BQL | | | Yes |
| Ethylene glycol monomethyl ether | 109-86-4 | 30 | BQL | BQL | | | Yes |
| Formaldehyde | 50-00-0 | 9.0*** | BQL | BQL | | | Yes |
| Hexane (n-) | 110-54-3 | 3,500 | BQL | BQL | | | Yes |
| Isophorone | 78-59-1 | 1,000 | BQL | BQL | | | Yes |
| Isopropanol | 67-63-0 | 3,500 | BQL | BQL | | | Yes |
| Methyl chloroform | 71-55-6 | 500 | BQL | BQL | | | Yes |
| Methyl t-butyl ether | 1634-04-4 | 4,000 | BQL | BQL | | | Yes |
| Methylene chloride | 75-09-2 | 200 | BQL | BQL | | | Yes |
| Naphthalene | 91-20-3 | 4.5 | BQL | BQL | | | Yes |
| Phenol | 108-95-2 | 100 | BQL | BQL | | | Yes |
| Propylene glycol monomethyl ether | 107-98-2 | 3,500 | BQL | BQL | | | Yes |
| Styrene | 100-42-5 | 450 | BQL | BQL | , | | Yes |
| Tetrachloroethylene (perchloroethylene) | 127-18-4 | 18 | BQL | BQL | | | Yes |
| Toluene | 108-88-3 | 150 | BQL | BQL | | | Yes |
| Trichloroethylene | 79-01-6 | 300 | BQL | BQL | | | Yes |
| Vinyl acetate | 108-05-4 | 100 | BQL | BQL | | | Yes |
| Xylenes (m-, o-, p-) | 1330-20-7 | 350 | BQL | BQL | | | Yes |

BQL denotes below quantifiable level of 2 µg/m³ (instrument calibration using authentic standard).

^{††}The emission factor (EF) is calculated from the chamber concentration (CC), the chamber air change rate (N_c), the chamber volume (V_c), and the product area exposed in the chamber (A_c) as: EF = (CC*V_c*N_c)/A_c.

^{*}Denotes compound is within volatility range of method but no calibration standard was available.

^{**}The predicted building exposure concentration (BC) is calculated from the emission factor (EF), the building air change rate (N_B), the building room volume (V_B), and the product area exposed in the building room (A_B) as: BC = (EF*A_B)/(V_B*N_B). Prediction based on a standard classroom sealant usage of 39 m in a 231 m³ room with 0.82 ACH or on a standard office sealant usage of 14.6 m in a 30.6 m³ room with 0.68 ACH.

^{***}Guidance value per CA Standard Method

November 21, 2017 Date Prepared: 18729-010AA Product #: Report #: 18729-01

©2017 UL LLC

TABLE 3

CHAMBER CONCENTRATIONS AND EMISSION FACTORS FOR TVOC AND FORMALDEHYDE AT 24, 48, AND 96 HOURS **FOLLOWING 10 DAYS OF CONDITIONING**

PREPARED FOR: EVERKEM DIVERSIFIED PRODUCTS INC PRODUCT 18729-010AA; SOUNDSEAL 90

| ELAPSED EXPOSURE HOUR AFTER 10 DAYS CONDITIONING | CHAMBER CONCENTRATION (µg/m³) | EMISSION FACTOR ^{††} (μg/m•hr) | | | | | |
|--|-------------------------------------|---|--|--|--|--|--|
| TVOC [†] | | | | | | | |
| 24 | 2,600 | 780 | | | | | |
| 48 | 2,500 | 750 | | | | | |
| 96 | 2,200 | 670 | | | | | |
| Formaldehyde [‡] | Formaldehyde [‡] | | | | | | |
| 24 | BQL | BQL | | | | | |
| 48 | BQL | BQL | | | | | |
| 96 | BQL | BQL | | | | | |

BQL denotes below quantifiable level of 2 µg/m³.

Exposure hours are nominal (\pm 1 hour). [†]Defined as the sum of those VOCs that elute between the retention times of n-hexane (C_6) and n-hexadecane (C_{16}) on a non-polar capillary

GC column quantified based on a toluene response factor.

[‡] Compound identified and quantified by DNPH derivitization and HPLC/UV analysis.

^{††}The emission factor (EF) is calculated from the chamber concentration (CC), the chamber air change rate (Nc), the chamber volume (Vc), and the product area exposed in the chamber (A_C) as: EF = $(CC^*V_C^*N_C)/A_C$.

Date Prepared: November 21, 2017 18729-010AA Product #: 18729-01 Report #:

©2017 UL LLC

TABLE 4

CHAMBER CONCENTRATIONS, EMISSION FACTORS, AND PREDICTED EXPOSURE CONCENTRATIONS FOR THE TVOC & TEN MOST ABUNDANT IDENTIFIED INDIVIDUAL VOLATILE ORGANIC COMPOUNDS (VOCs) AND/OR ALDEHYDES AT 96 HOURS FOLLOWING 10 DAYS OF CONDITIONING

PREPARED FOR: EVERKEM DIVERSIFIED PRODUCTS INC PRODUCT 18729-010AA; SOUNDSEAL 90

| CAS NUMBER | COMPOUND | CHAMBER CONC. (µg/m³) | EMISSION FACTOR ^{††} (μg/m•hr) | CALCULATED EXPOS CONCENT (µg/ | SURE RATION** |
|---------------|------------------------------------|-----------------------------|---|--|------------------|
| | | | | Classroom | Office |
| | TVOC ^{TT} | 2,200 | 670 | 140 | 470 |
| | Unresolved hydrocarbons | 970 | 290 | 59 | 200 |
| 1120-21-4 | Undecane | 220 | 67 | 14 | 47 |
| 124-18-5 | Decane | 190 | 57 | 12 | 40 |
| 57-55-6 | 1,2-Propanediol (Propylene glycol) | 190 | 57 | 12 | 40 |
| 112-40-3 | Dodecane | 97 | 29 | 5.9 | 20 |
| 111-84-2 | Nonane | 90 | 27 | 5.5 | 19 |
| 2847-72-5 | Decane, 4-methyl | 56 | 17 | 3.5 | 12 |
| 1678-93-9 | Cyclohexane, butyl* | 43 | 13 | 2.6 | 8.8 |
| 5911-04-6 | Nonane, 3-methyl* | 40 | 12 | 2.5 | 8.4 |
| 1678-92-8 | Cyclohexane, propyl* | 35 | 10 | 2.1 | 7.3 |

Exposure hours are nominal (± 1 hour)

VOC data obtained by scanning GC/MS; identification of compound made by retention time and mass spectral characteristics.

[†]Quantified using multipoint authentic standard curve. Other VOCs quantified relative to toluene.

^{*}Identification based on NIST mass spectral database only.

 $^{^{\}ddagger}$ Compound identified and quantified by DNPH derivitization and HPLC/UV analysis.

^{††}The emission factor (EF) is calculated from the chamber concentration (CC), the chamber air change rate (N_C), the chamber volume (V_C), and the

product area exposed in the chamber (A_c) as: EF = $(CC^*V_c^*N_c)/A_c$.

The product area exposed in the chamber (A_c) as: EF = $(CC^*V_c^*N_c)/A_c$.

The product area exposed in the chamber (A_c) as: EF = $(CC^*V_c^*N_c)/A_c$. quantified based on a toluene response factor.

^{**}The predicted building exposure concentration (BC) is calculated from the emission factor (EF), the building air change rate (N_B), the building room volume (V_B), and the product area exposed in the building room (A_B) as: BC = (EF*A_B)/(V_B*N_B). Prediction based on a standard classroom sealant usage of 39 m in a 231 m³ room with 0.82 ACH or on a standard office sealant usage of 14.6 m in a 30.6 m³ room with 0.68 ACH.

Date Prepared: November 21, 2017 Product #: 18729-010AA Report #: 18729-01

©2017 UL LLC

TABLE 5

VOC PREDICTED AIR CONCENTRATIONS AND REGULATORY INFORMATION AT 96 HOURS FOLLOWING 10 DAYS OF CONDITIONING

PREPARED FOR: EVERKEM DIVERSIFIED PRODUCTS INC PRODUCT 18729-010AA; SOUNDSEAL 90

| CAS | COMPOUND IDENTIFIED | CHAMBER EMISSION PREDICTED EXPOSURE CONCENTRATION** | | | NDICATE NCE ON | | | |
|---------|--|---|-----------------------------------|-----------|-------------------|---------|--------|------|
| NUMBER | COMPOUND IDENTIFIED | CONC. (µg/m³) | FACTOR ^{††} (µg/m•hr) | (µg | /m³) | CA PROP | CA AIR | CREL |
| | | | 0 | Classroom | Office | 65 | TOXIC | |
| 71-36-3 | 1-Butanol (N-Butyl alcohol) [™] | 16 | 4.7 | 1.0 | 3.3 | | √(IVB) | |

[†]Quantified using multipoint authentic standard curve. Other VOCs quantified relative to toluene.

CAL Prop. 65: California Health and Welfare Agency, Proposition 65 Chemicals

- 1 = known to cause cancer
- 2 = known to cause reproductive toxicity

CAL Toxic Air Contaminant:

- 1) Substances identified as Toxic Air Contaminants, known to be emitted in California, with a full set of health values reviewed by the Scientific Review Panel.
- IIA) Substances identified as Toxic Air Contaminants, known to be emitted in California, with one or more health values under development by the Office of Environmental Health Hazard Assessment for review by the Scientific Review Panel.
- IIB) Substances NOT identified as Toxic Air Contaminants, known to be emitted in California, with one or more health values under development by the Office of Environmental Health Hazard Assessment for review by the Scientific Review Panel.
- III) Substances known to be emitted in California, and are NOMINATED for development of health values or additional health values.
- IVA) Substance identified as Toxic Air Contaminants, known to be emitted in California, and are TO BE EVALUATED for entry into Category III.
- IVB) Substance NOT identified as Toxic Air Contaminants, known to be emitted in California, and are TO BE EVALUATED for entry into Category III.
- V) Substance identified as Toxic Air Contaminants, and NOT KNOWN TO BE EMITTED from stationary source facilities in California based on information from the AB 2588 Air Toxic "Hot Spots" Program and the California Toxic Release Inventory.
- VI) Substances identified as Toxic Air Contaminants, NOT KNOWN TO BE EMITTED from stationary source facilities in California, and are active ingredients in pesticides in California.

Chronic REL: California Office of Environmental Health Hazard Assessment (OEHHA), Chronic Reference Exposure Levels

✓ = Found in Listing

[‡]Compound identified and quantified by DNPH derivitization and HPLC/UV analysis.

^{††}The emission factor (EF) is calculated from the chamber concentration (CC), the chamber air change rate (N_C), the chamber volume (V_C), and the product area exposed in the chamber (A_C) as: EF = (CC*V_C*N_C)/A_C.

^{**}The predicted building exposure concentration (BC) is calculated from the emission factor (EF), the building air change rate (N_B), the building room volume (V_B), and the product area exposed in the building room (A_B) as: BC = (EF*A_B)/(V_B*N_B). Prediction based on a standard classroom sealant usage of 39 m in a 231 m³ room with 0.82 ACH or on a standard office sealant usage of 14.6 m in a 30.6 m³ room with 0.68 ACH.

Date Prepared: November 21, 2017
Product #: 18729-010AA
Report #: 18729-01

©2017 UL LLC

REFERENCES

- 1. The State of California's Indoor Air Quality Program, "Standard Method for the Testing and Evaluation of Volatile Organic Chemical Emissions from Indoor Sources using Environmental Chambers" Version 1.2. https://archive.cdph.ca.gov/programs/IAQ/Documents/CDPH-IAQ StandardMethod V1 2 2017.pdf.
- 2. ASTM D 5116, "Standard Guide for Small-Scale Environmental Chamber Determinations of Organic Emissions from Indoor Materials/Products." ASTM, West Conshohocken, PA, 2010.
- 3. EPA TO-17, "Compendium of Methods for the Determination of Toxic Organic Compounds in Ambient Air Second Edition," United States Environmental Protection Agency, www.epa.gov/ttn/amtic/files/ambient/airtox/to-17r.pdf, 1999.
- 4. ASTM D 6196 "Practice for the Selection of Sorbents and Pumped Sampling/ Thermal Desorption Analysis Procedures for Volatile Organic Compounds in Air." ASTM, West Conshohocken, PA, 2009.
- 5. ASTM D 5197, "Test Method for Determination of Formaldehyde and Other Carbonyl Compounds in Air (Active Sampler Methodology)." ASTM, West Conshohocken, PA, 2009.
- ISO 16000-6, "Indoor air -- Part 6: Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA sorbent, thermal desorption and gas chromatography using MS/FID," 2004. http://www.iso.org/iso/iso_catalogue/catalogue_tc/catalogue_detail.htm?csnumber=30147.
- 7. California Environmental Protection Agency; Chronic Reference Exposure Levels; The Office of Environmental Health Hazard Assessment (OEHHA); http://www.oehha.ca.gov/air/Allrels.html.
- 8. California Environmental Protection Agency. Safe Drinking Water & Toxic Enforcement Act of 1986 (Proposition 65): No Significant Risk Levels for Carcinogens; Acceptable Intake Levels for Reproductive Toxicants (Status Report). Sacramento: California Environmental Protection Agency; http://www.oehha.ca.gov/prop65/getNSRLs.html.
- 9. California Environmental Protection Agency. Air Resources Board. Toxic Air Contaminants (TAC) Identification List; http://www.arb.ca.gov/toxics/cattable.htm

©2017 UL LLC

APPENDIX 1 PREPARED FOR: EVERKEM DIVERSIFIED PRODUCTS INC PRODUCT 18729-010AA; SOUNDSEAL 90



Report #: ©2017 UL LLC

APPENDIX 2

CHAIN OF CUSTODY

| (II) | UL Environment Ch | | |
|--------------------------------------|---|---|--|
| | 10002 | 4331 | |
| FOR INTERNAL USE ONLY | | Test Information | |
| | Proposal # | Specialized Test for Odors | Formaldehyde Only 4 Hr 24 Hr |
| CUR/BG494 | RUSH (Confirm with Account Manager prior to submitting product) | CA 01350 CDPN/EHLB/Standard Method V) 1 | CfficeClassroomResidential |
| 0ject - Product # 18729 - 0 10 AA | 24 Hr TVOC with Formaldehyde | | erIntermediate Chember Large Chamber |
| All Sculpts | 24 Hr TVOC & IVOCs with Formaldehyde | Other (Specify test method, non-standard sam products, etc.): | ple preparation, modeling perameters, application rate for wet |
| Cal | GREENGUARD Screening Test (24 Hr TVOC, IVOCs, and Aldehydes w/modeling) | | |
| isu. | Manufacture | and Cantact Details | 11 |
| ompany Name | Everten | Contact Name | David Genell |
| treet Address | 5150 Indiana Area | Title | Rudby Assumme Director |
| riv State/Province, Zip/Postal Code | Whyter-Salem, NC, 27106 | Phone Number | 14900-636-3160 |
| | USA | E-Mail Address | agained @ eventon productale |
| ountry | 760 | duct details | |
| ample ID (Used in Report) | Sound Seal 90 | Product Collection Location | Post Production Storage |
| reduct Commercial Name | Sound Seal 90 | Product Collection Date/Time (mm/dd/yyyy/ht/mm) | 10/13/2017/11:00 |
| fanufacturer's Identification Number | 172701 | Product Collected By | David Gorrell |
| fanulactured Date (mm/dd/yyyy) | 03/14/2-97 | Number of Product Pieces | 126.2 + |
| STUINCING DATE (INTOCO7777) | Post Tee | ting Instructions | |
| Denor Brothet / Pehim Shilper and | Manufacturer's Shipping Account # must be provided for product n | eturn) | Discard product after testing |
| | | Manufacturer's Shipping Accit # | + 1+1 |
| Return Shipper | | Carner | POPEL |
| Packed By | 10/13/17 | Air Bill # | 7431 7274 6154 |
| Ship Date (mm/dd/yyyy) | | Tracking Details | |
| Relinquished By (Manufacturer) | | Date 3. Time (mm/dd/yyyy/hh:mm) | |
| | | | |
| ignature | O shoratow Receiving Dr | talls - FOR INTERNAL USE ONLY | |
| eceived by (Laboratory) | I Inapport | Date & Time (mm/dd/yyyy/hir.mm) | 10/16/17 9:31 NO |
| Signature | Say motor | | |
| Types of Containers | ench | Shipping Package Notes | |
| Condition of Shipping Package | Lundamaged Damaged | Product Condition Notes | |
| serie con semblement or con | AcceptableUnscraptable | | |

©2017 UL LLC

APPENDIX 3

QUALITY CONTROL PROCEDURES FOR ENVIRONMENTAL CHAMBER EVALUATIONS

UL Environment's IAQ testing laboratories are ISO/IEC 17025 accredited with defined and executed internal and third party verification programs encompassing emission test methods and low level pollutant measurements. UL Environment's quality control/assurance plan is designed to ensure the integrity of the measured and reported data obtained during its product evaluation studies. This QC program encompasses all facets of the measurement program from sample receipt to final review and issuance of reports. As a firm with ISO/IEC 17025 accredited IAQ testing laboratories, UL Environment's product control, testing, data handling, and reporting protocols and procedures are standardized and controlled. UL Environment participates in proficiency and accreditation measurement programs for VOC and emission testing as required by the State of California, Germany Ministry of Health's Blue Angel Program, LGC Standards Air Proficiency Testing Scheme, and GREENGUARD Certification programs. Quality Assurance is maintained through UL Environment's computerized data management system. An electronic "paper trail" for each analysis is also maintained and utilized to track the status of each sample, and to store the results. A complete quality report can be provided upon request and all test data and analysis procedures are available on site for customer review.

Chamber Evaluations

One of the most critical parameters in UL Environment's product evaluations is the measurement of ultratrace levels of gaseous chemicals, typically in the ppb air concentration range. This necessitates a very rigidly maintained effort to control background contributions and contamination. These contributions must be significantly less than those levels being measured for statistically significant data to be obtained. UL Environment addresses this control in many directions including chamber construction materials, air purification and humidification, sampling materials and chemicals, sample introduction, and analysis.

Supply air purity is monitored on a weekly basis, using identical methodology to the chamber testing. The supply air is assured to contain less than 10 $\mu g/m^3$ TVOC, < 10 $\mu g/m^3$ total particles, < 2 $\mu g/m^3$ formaldehyde, and < 2 $\mu g/m^3$ for any individual VOC. Preventative maintenance ensures supply air purity, and corrective action is taken when any potential problems are noted in weekly samples. Supply air filter maintenance is critical for ensuring the purity of the chamber supply air. Chamber background samples are obtained prior to product exposure to ensure contaminant backgrounds meet the required specifications prior to product exposure. Results of this monitoring are maintained at UL Environment and available for on-site inspection.

All environmental chamber procedures are in accordance with ASTM D 5116 and meet the data quality objectives required.

Various measures are routinely implemented in a product's evaluation program. These include but are not limited to:

appropriate record keeping of sample identifications and tracking throughout the study;

Date Prepared: November 21, 2017
Product #: 18729-010AA
Report #: 18729-01

©2017 UL LLC

- calibration of all instrumentation and equipment used in the collection and analysis of samples;
- validation and tracking of all chamber parameters including air purification, environmental controls, air change rate, chamber mixing, air velocities, and sample recovery;
- analysis of spiked samples for accuracy determinations;
- duplicate analyses of 10% of all samples evaluated and analyzed;
- multi-point calibration and linear regression of all standardization;
- analysis of controls including chamber backgrounds, sampling media, and instrumental systems.

VOC and Aldehyde Measurements

Precision of TVOC and aldehyde analyses is assessed by the Relative Standard Deviation (%RSD) from duplicate samples, defined as the standard deviation of each data set divided by the mean multiplied by 100. All QC data measurements are calculated based on the 12 month period indicated below. The VOC accuracy is based on recovery of toluene mass spiked onto sorbent material. The aldehyde accuracy is based on LGC Standard formaldehyde proficiency test results, measured by the mean Relative Percent Difference (%RPD). Third party proficiency and round robin testing for low level VOCs for national and international programs are continuously conducted and reported in UL Environment's quarterly Quality Assurance Report, and are available to all customers.

| 12 Month Period | November 1, 2016 through October 31, 2017 | |
|----------------------|---|-------|
| Precision Mean RSD % | TVOC | 6.3 |
| Precision Wean RSD % | Total Aldehydes (Including Formaldehyde) | 3.9 |
| Acquirocy 9/ | VOC – Toluene Recovery | 100.5 |
| Accuracy % | Formaldehyde Mean RPD | 2.4 |